



FINES

- Type of product: direct shipping
- Mine: Kédia and M'Haoudat
- Loading port: Nouadhibou ore port

TZF

Chemical test

ELEMENT	%
Fe	64,50
Fe++	0,50
SiO2	6,00
Al2O3	1,00
P	0,05
LOI	0,60
H2O	1,50

Grain gradation

< 0,150 : 32 %
> 8 mm: 8.00 %
D50 = 1,25 mm
D80 = 6,00 mm

TZFC

Chemical test

ELEMENT	%
Fe	62,00
Fe++	1,15
SiO2	8,80
Al2O3	0,90
P	0,070
LOI	0,70
H2O	1,50

Grain gradation

< 0,150 mm : 31.5 %
> 8 mm : 6.00 %
D50 = 0,560 mm
D80 = 4,500 mm

XFC

Chimi

ELEMENT	%
Fe	
Fe++	
SiO2	
Al2O3	
P	
LOI	
H2O	

Grain

< 0,15
> 8 m
D50 =
D80 =